
PROBLEM SOLVING GUIDE

Marks





OPTIONS

STEPS



- 1. SHAKE WELL BEFORE EACH USE.
- SWEEP OR VACUUM SURFACE TO BE CLEANED TO REMOVE ANY LOOSE CONTAMINANTS.
- 3. APPLY **ELITE CLEANER** LIBERALLY ON SURFACE TO BE CLEANED DIRECTLY FROM BOTTLE OR WITH A SPONGAUSA™ SPONGE, OR A BRUSH OR SCRUB MACHINE.
- 4. ALLOW ELITE CLEANER TO DWELL ON SURFACE FOR UP TO 5 MINUTES.
- 5. AGITATE WITH A PRIMO TOOLS™ WHITE NYLON SCRUB PAD, OR A BRUSH OR OTHER COMPARABLE NON-MARRING SCRUBBING TOOL UNTIL CONTAMINATE OR STAIN IS REMOVED.
- **6.** Thoroughly rinse surface with water. A wet/dry vacuum may also be used.

EXPERT TIP: HIGH-PRESSURE (1000–3000 PSI) SPRAYERS ARE HIGHLY EFFECTIVE AT RINSING AWAY CONTAMINATES AND STAINS WHEN USED IN CONJUNCTION WITH **ELITE CLEANER**.


- 7. WIPE SURFACE COMPLETELY DRY USING A CLEAN, DRY, WHITE COTTON OR MICRO-FIBER TOWEL.
- 8. If surface is to be sealed, allow 24 hours drying time prior to applying a high quality OMNI sealer.



200 to 2,000


SQ. FT. PER

GALLON



2. Apply Sealer Remover using a SpongaUSA™ sponge or a mop, paint-pad applicator, paint roller, or brush.

Expert Tip: When using **Sealer Remover** on large projects, divide working area into manageable sections of approx. 25 sq. ft.



4. Agitate with a Primo Tools™ White Nylon Scrub Pad or other comparable non-marring scrubbing tool until achieve desired results.

Expert Tip: High-pressure (1000 – 3000psi) sprayers are highly effective at achieving desired results when used in conjunction with **Sealer Remover**.

- 5. Wipe surface completely dry using a clean, dry, white cotton towel or micro-fiber towel.
- **6.** If surface is to be sealed, allow 24 hours drying time prior to applying a high quality OMNI sealer. **Expert Tip: Sealer Remover** may damage synthetic tile or other solvent sensitive surfaces.



COVERAGE 75 to 2,000

SQ. FT. PER

GALLON

- 1. SWEEP OR VACUUM SURFACE TO BE CLEANED TO REMOVE ANY LOOSE CONTAMINANTS.
- 2. MIX POULTICE STAIN REMOVER WITH WATER TO FORM A THICK PASTE.

EXPERT TIP: CAN USE DEEP CLEANER OR HEAVY DUTY CLEANER IN PLACE OF WATER FOR ENHANCED PERFORMANCE.

- **3.** APPLY **POULTICE STAIN REMOVER** PASTE APPROXIMATELY $\frac{1}{4}$ " THICK TO STAINED SURFACE. ALLOW PASTE TO EXTEND BEYOND THE EDGES OF THE STAIN BY AT LEAST 1".
- 4. COVER PASTE WITH PLASTIC AND TAPE EDGES OF PLASTIC TO SURFACE WITH PAINTER'S-TYPE TAPE.
- **5.** ALLOW PASTE TO DWELL ON SURFACE UNDER PLASTIC FOR 24 TO 48 HOURS.
- **6.** REMOVE THE PLASTIC COVERING THE PASTE.
- 7. REMOVE PASTE WITH A NON-MARRING TOOL (PLASTIC PUTTY KNIFE).
- **8.** After stain has been removed, clean paste with a SpongaUSA™ Sponge, or a white, cotton or micro-fiber towel and water.
- 9. THOROUGHLY RINSE SURFACE WITH WATER & DRY WITH A WHITE COTTON OR MICRO-FIBER TOWEL. A WET/DRY VACUUM MAY ALSO BE USED.
- 10. Some surfaces may require additional applications.
- 11. If surface is to be sealed, allow 24 hours drying time prior to applying a high quality OMNI sealer.



Technical Support: 949-709-5270 Mon thru Fri 6:00am PT to 4:00pm PT and/or E-mail TechSupport@OMNI-Sealers.com.

Problem Solving Guide is a general recommendation. Actual results may vary. Read product directions thoroughly before use.

ALWAYS TEST IN A SMALL INCONSPICUOUS AREA.